

-1- (JAPIO)

ACCESSION NUMBER  
TITLE

PATENT APPLICANT  
INVENTORS

PATENT NUMBER  
APPLICATION DETAILS  
SOURCE

INT'L PATENT CLASS  
JAPIO CLASS  
ABSTRACT

85-262353

MANUFACTURE OF NEGATIVE ZINC ALLOY POWDER FOR  
ALKALINE BATTERY

(2000353) TOSHIBA BATTERY CO LTD  
FURUSHIMA, KAZUO; TERAOKA, HIROKIMI; MIYASAKA,  
KOJIRO; YOSHIDA, KAZUMASA

85.12.25 J60262353, JP 60-262353

84.06.07 84JP-115481, 59-115481

86.05.17 SECT. E, SECTION NO. 404; VOL. 10, NO. 133,  
PG. 49.

H01M-004/42; H01M-004/12

42.9 (ELECTRONICS--Other)

PURPOSE: To obtain a negative zinc alloy powder which greatly suppresses the generation of hydrogen gas by subjecting an electrolyte solution containing elements for constituting the negative powder to electrolysis to deposit the elements on the surface of the negative electrode and then melting and atomizing the resulting electrodeposited material to pulverize it.

CONSTITUTION: An electrolyte solution containing elements for constituting a zinc alloy of a desired composition is prepared. Next, while the temperature of the solution is properly maintained, electrolysis is performed with a given current density to deposit the elements on the surface of a negative electrode. A positive electrode made of carbon is usually used and an aluminum electrode with a smooth surface is used as the negative electrode. The thus electrodeposited cake composed of the elements is then molten and atomized to alloy and pulverize the whole cake. During this process, the particle diameter of the alloy powder is controlled by properly selecting atomization conditions such as hole diameter, atomization pressure and molten zinc temperature. By the means mentioned above, it is possible to minimize variation in the content of lead over its certain range.